

Cl/SfB		Yt3
CAW Z20		
Uniclass L6732:P74		

Description

CT113 is a viscous liquid adhesive made from a blend of synthetic rubber and resins. It was developed for the bonding of illbruck EPDM membranes.

Colour

Black

Packaging

4.7 kg pail

Technical Information

Property	Classification
Composition	A blend of synthetic rubber and resin
System	Solvent evaporation
Specific Gravity	0.8
Drying Time (at 20°C)	approx. 20 minutes
Dry Tack Time (at 20°C)	
Consumption	
Final Adhesion Strength	24-48 hours
Peel Strength	50 N / 25 mm
Application Temperature	+5°C up to +35°C
Service Temperature	-20°C up to +80°C
Storage Temperature	
Storage	Store in dry shaded conditions between +5°C and +25°C.
Shelf Life	12 months when stored as recommended in original unopened packaging.

Necessary Tools

- Installation requires the use of a tape measure, scissors, cutter, brush, seam roller, container for adhesive dilution, mixing tool, solvent (AW421). In certain cases, adhesive tape may be required for temporary fixing of membranes.

Preparation

- Always carry out a test to confirm compatibility prior to use.
- All surfaces must be dry, clean and sound, free from dirt, grease and other contamination.
- Use mechanical abrasion to clean porous surfaces if necessary before sealing.
- It is recommended to degrease the substrate (and membrane if necessary) by using isopropanol.



CT113

EPDM Membrane Adhesive

Usage / Purpose

CT113 is a viscous adhesive developed for the bonding of ME220 EPDM membranes, particularly in façade applications. CT113 is compatible with surfaces such as wood, metal, masonry and other building materials.

Key Benefits

- Ideal for bonding of ME220 EPDM membranes in facade installations
- Cured adhesive has excellent resistance to weathering and the ageing effects of UV exposure
- Adhesive accommodates a wide fluctuation in temperature from -20°C up to +80°C
- Cures within 20 minutes to form a high strength and elastomeric connection
- High initial adhesion strength

Priming

- Porous substrates may need to be primed. As a primer, dilute CT113 in ratio 1 part CT113 to 2 – 3 parts AW421 solvent (by volume).
- Apply primer onto porous materials using brush or roller to the whole of the final bonded area (Fig.1).
- Application of the adhesive must be delayed until after the primer is fully cured (10 – 30 min).
- Use a separate container for the primer dilution and never return the remaining mixed material into the CT113 adhesive.
- The use of primer onto porous materials not only improves adhesion but also reduces consumption of adhesive and substantially extends the processing time which is beneficial especially on hot summer days.

Application

- Adhesive must be mixed thoroughly before application.
- Apply CT113 using a brush or roller evenly to both surfaces to be bonded (see Fig. 2).
- After applying the adhesive, allow to flash off (approx. 10 – 15 min using finger touch test). This is very important to ensure good adhesion.
- After flashing off, both bonded surfaces must be connected and the top layer must be pressed thoroughly using a seam roller.
- In the case of heavier strips, the membrane must be fixed temporarily until sufficient adhesive loading capacity is achieved.
- The recommended bonded width between membranes and porous surfaces (concrete, brick, etc.) is minimum 100 mm. A 20 – 30 mm overlap is recommended for non-porous surface bonding.
- In case of unwanted thickening of the adhesive, dilute with AW421 solvent and mix until homogeneous. The amount of solvent added must not exceed 10%.
- For sealing of overlaps and membrane connections, use OT015 Adhesive. Connections of membranes to asphalt or PVC hydro - insulation foils must be made with a metal cover plate. In the case of bonding between membrane and styrene foam, use illbruck OT008 paste adhesive.

Coverage

As adhesive: 94 m @ 100 mm width / 4.7 kg unit
(applied to membrane and substrate)

As primer: 329 m @ 100 mm width / 4.7 kg unit
(diluted 3 : 1 with AW421).

Cleaning

Clean tools and any uncured adhesive with AT200 High Strength Cleaner. Cured adhesive can only be removed mechanically.

Please Note

Solvents contained within the adhesive may damage sensitive surfaces. The adhesive is not suitable for direct application onto polystyrene, PVC, asphalt or bitumen.

Health & Safety Precautions

Safety data sheet must be read and understood before use.




Figure 1




Figure 2

Technical Service

tremco illbruck has a team of experienced Technical Service Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Service on 0191 419 0505.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which

has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. tremco illbruck Ltd. reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



tremco illbruck Limited
3A Walton Road, Pattinson North
NE38 8QA Washington
T: +44 191 419 0505
F: +44 191 419 2200

uk.sales@tremco-illbruck.com
www.tremco-illbruck.co.uk